

Test With .5 Ounce Cloth And Z-Poxy Finishing Resin.

All Panels 4" x 6" or 24sq"

2K Primer was Nason 421-19 mixed 4:1 with 483-87 activator and reduced 10% with 441-21 reducer

Epoxy was Nason 491-16 mixed 1:1 with 483-19 catalyst

All colors DuPont Chromabase reduced 1:1 with 7160 Basemaker

Clear was Nason 496-00 mixed 4:1 with 483-79 activator then reduced 10% with 441-21 reducer

Bare Weight	Hairspray Y/N	1 st Coat Resin Sanded with 120 then 220	2 nd Coat Resin Sanded with 120 then 220	Primer Sanded Down To 600 grit	Paint	Total Weight Gain
6.0 g	No	7.6g	7.6g	8.0g 2 coats Epoxy sanded mostly off	9.3g White	3.3g
6.2g	No	7.8g	7.8g	8.6g 2 coats Thinned 2K	10.2g White	4.0g
6.1g	Yes	7.7g	7.6g	8.5g 2 coats Thinned 2K	9.4g Silver	3.3g
6.2g	No	7.7g	7.6g	8.3g 2 coats Thinned 2K Sanded mostly off	9.1g Silver	2.9g
6.9g	Yes	8.4g	8.3g	8.9g 2 coats Epoxy	9.7g Blue Metallic	2.8g
5.6g	No	7.3g	7.3g	7.8g 2 coats Epoxy	8.6g Blue Metallic	3.0g